

BEST AVAILABLE COPY

P1 1044249

REC'D 01 AUG 2003

WIPO

PCT

# THE UNITED STATES OF AMERICA

**TO ALL TO WHOM THESE PRESENTS SHALL COME:**

UNITED STATES DEPARTMENT OF COMMERCE  
United States Patent and Trademark Office

July 25, 2003


THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/391,012 ~

FILING DATE: June 23, 2002 /

RELATED PCT APPLICATION NUMBER: PCT/US03/19984

By Authority of the  
COMMISSIONER OF PATENTS AND TRADEMARKS



*H. Phillips*  
H. PHILLIPS  
Certifying Officer

## PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

06/23/02

6-23-02  
PROVISIONAL APPLICATION COVER SHEET  
This is a request for filing a PROVISIONAL APPLICATION under 37 CFR 1.53(b)(2)

EXPRESS MAIL MAILING LABEL

Number: **RU 633791507 US** Date of Deposit: **June 23, 2002**

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R. 1.10 on the date indicated above and is addressed to the Commissioner of Patents and Trademarks, Washington, D.C. 20231, on **June 23, 2002**

Typed or Printed Name: **Maria S. Swiatek**

Signed: *Maria Swiatek*

Docket Number

P-71606-1/MSS

Type a plus sign (+) inside this box -

11836 U.S. PTO  
60/39102

INVENTOR(s)/APPLICANT(s)					
LAST NAME	FIRST NAME	MIDDLE INITIAL	RESIDENCE (CITY AND EITHER STATE OR FOREIGN COUNTRY)		
Helms	Aubrey		Los Gatos, California		
Kapkin	Kerem		Watsonville, California		
Lee	Sing-In		Scotts Valley, California		
Senzaki	Yoshihide		Aptos, California		
TITLE OF THE INVENTION (280 characters max)					
<b>Method and System for Photo-Assisted Atomic Layer Deposition and Removal</b>					
CORRESPONDENCE ADDRESS					
Dorsey & Whitney LLP, 4 Embarcadero Center, Suite 3400, San Francisco					
STATE	CA	ZIP CODE	94111	COUNTRY	US
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/>	Specification	Number of Pages	10 total	<input type="checkbox"/>	Small Entity Statement
<input checked="" type="checkbox"/>	Drawings	Number of Sheets	15	<input checked="" type="checkbox"/>	Other (specify):
					1 page(s) of Claims
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)					
<input type="checkbox"/>	A check or money order is enclosed to cover the Provisional filing fees			PROVISIONAL FILING FEE AMOUNT (\$)	\$160.00
<input checked="" type="checkbox"/>	The Commissioner is hereby authorized to charge filing fees and credit Deposit Account Number:			06-1300 (Order No. P-71606-1/MSS)	

The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.

☒ No.

☐

Yes, the name of the U.S. Government Agency and the Government contract number are: \_\_\_\_\_

Respectfully submitted,

SIGNATURE:

*Maria Swiatek*

Date

June 23, 2002

TYPED or PRINTED NAME **Maria S. Swiatek**

REGISTRATION NO.  
(if appropriate)

37,244

☐

Additional inventors are being named on separately numbered sheets attached hereto.

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

Burden Hour Statement: This form is estimated to take .2 hours to complete. Times will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Assistant Commissioner for Patents, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231. 1043634

## METHOD AND SYSTEM FOR PHOTO-ASSISTED ATOMIC LAYER DEPOSITION AND REMOVAL

### FIELD OF THE INVENTION

5           The present invention relates generally to the field of semiconductors. More specifically, the present invention relates to photo-assisted atomic layer deposition and removal of films on semiconductor devices and wafers.

### BACKGROUND OF THE INVENTION

10           Semiconductor devices of future generation require thinner dielectric films for MOS transistor gates, and capacitor dielectrics. As oxides are scaled down, the tunneling leakage current becomes significant and limits the useful range for gate oxides to about 1.8 nm or more.

          High dielectric constant metal oxides such as  $\text{HfO}_2$  ( $k=20$ ),  $\text{ZrO}_2$  ( $k=20$ ) and Hf and Zr silicates are considered alternative materials to silicon oxide ( $k=3.9$ ) to provide gate dielectrics with high capacitance without compromising the leakage current. However, prior art deposition techniques such as chemical vapor deposition (CVD) are increasingly unable to meet the requirements of advanced thin films. While CVD processes can be tailored to provide conformal films with improved step coverage, CVD processes often require high processing temperatures, result in incorporation of high impurity concentrations, and have poor precursor or reactant utilization efficiency. For instance, one of the obstacles of making high  $k$  gate dielectrics is the formation of an interfacial silicon oxide layer during CVD processes. Another obstacle is the limitation of prior art CVD processes in depositing ultra thin films for high  $k$  gate dielectrics on a silicon substrate.

20           Atomic layer deposition (ALD) is an alternative to traditional CVD processes to deposit very thin films. ALD has several advantages over traditional CVD. ALD can be performed at comparatively lower temperatures which is compatible with the industry's trend toward lower temperatures, has high precursor utilization efficiency, and can produce conformal thin film layers. More advantageously, ALD can control film thickness on an atomic scale, and can be used to "nano-engineer" complex thin films. Accordingly, further developments in ALD are

highly desirable.

### SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide a method and system of forming films on semiconductor devices and wafers by photo-assisted atomic layer deposition and removal.

It is an another object of the present invention to provide a method of depositing a metal containing film on a substrate without forming an interfacial oxide layer between the metal containing film and the substrate.

It is another aspect of the present invention to provide a method of removing a material (dielectric or metal) at low temperatures.

In one aspect of the invention, there is provided a method of photo atomic layer deposition (PALD) of a film on a substrate. According to the PALD method of the invention, a substrate having an film deposited on the surface of the substrate is first pre-treated to form a stable, activated surface. The substrate having a stable, activated surface is then placed into a reactor maintained at a low temperature and high vacuum. A first gaseous precursor is introduced into the reactor about the substrate. The gas and substrate are exposed to a first pulse of electromagnetic irradiation and radical species are formed. The radicals react with the activated surface to terminate the surface with the radical species. Then a second precursor is introduced into the reactor and a second pulse of electromagnetic irradiation is initiated to form different radicals from the second precursor. The different radicals react with the terminated surface to form an atomic layer of material on the surface of the substrate.

### BRIEF DESCRIPTION OF THE FIGURES

The foregoing and other objects of the invention will be more clearly understood from the following description when read in conjunction with the accompanying drawings in which:

Figure 1 is a schematic view illustrating an interfacial silicon oxide layer formed between a metal containing layer and silicon substrate during a prior art deposition process.

Figure 2 is a schematic view illustrating a reactor for carrying out the photo atomic layer deposition method according to one embodiment of the present invention.

Figure 3 is a schematic view illustrating an alternative reactor for carrying out the photo atomic layer deposition method according to another embodiment of the present invention.

Figures 4A to 4J are schematic diagrams illustrating the steps of atomic layer exchange for formation of a SEOT gate dielectric according to another embodiment of the present invention.

Figures 5 and 6 are tables showing examples of liquid Hf precursors and liquid Zr precursors, respectively.

Figure 7 is a chart describing example applications for high  $\kappa$  gate dielectrics.

### DETAILED DESCRIPTION OF THE INVENTION

In general, the present invention provides a method and system of forming films on semiconductor devices and wafers by photo-assisted atomic layer deposition and removal. More specifically, in one embodiment of the present invention, a method of photo atomic layer deposition (PALD) of a film on a substrate is provided. The PALD method of the invention may be carried out as follows: a substrate having an film deposited on the surface of the substrate is first pre-treated to form a stable, activated surface. The substrate having a stable, activated surface is then placed into a reactor or chamber maintained at a low temperature and high vacuum. A first gaseous precursor is introduced into the reactor about the substrate. The gas and substrate are exposed to a first pulse of electromagnetic irradiation and radical species are formed. The radicals react with the activated surface to terminate the surface with the radical species. Then a second precursor is introduced into the reactor and a second pulse of electromagnetic irradiation is initiated to form different radicals from the second precursor. The different radicals react with the terminated surface to form an atomic layer of material on the surface of the substrate.

As illustrated in FIG. 1, an undesired interfacial silicon oxide layer is commonly formed between a metal oxide and silicon substrate during prior art depositions. One way to provide a clean interface between the metal oxide and silicon substrate is to perform a deposition process at a low temperature ranging from 120-150 °C. However, chemical molecules are usually not

activated at such low deposition temperatures. The present invention provides a solution to this problem by carrying out a photo-assisted atomic layer deposition at a low temperature and high vacuum, thus providing a clean interface between the metal oxide film and substrate.

The present invention is further described with reference to FIGs. 2 and 3 which schematically illustrates a high vacuum, low temperature reactor that can be used to perform photo-assisted atomic layer deposition of the invention. While a specific reactor is shown for illustrative purpose, other reactor designs may be used and the present method is not limited to any one reactor or chamber design. The present PALD method can be performed in any suitable reactors such as a single wafer reactor and multiple wafer reactor. The pressure within the reactor is maintained under vacuum, and preferably is below 1 torr.

In an illustrative example of the method and system of the present invention, a substrate having an oxide film deposited on the surface of the substrate is first pre-treated to form a hydrogen-terminated surface. The substrate having a hydrogen-terminated surface is then placed in a reactor maintained at a low temperature and high vacuum. An oxygen containing gas is introduced into the reactor above the substrate and a first pulse of electromagnetic irradiation is imposed to the oxygen containing gas to form oxygen radicals. The oxygen radicals react with the hydrogens at the silicon dangling bonds at the hydrogen-terminated surface. An oxygen terminated surface is formed after atomic layer exchange between the hydrogen and oxygen. Then a metal precursor is introduced into the reactor and a second pulse of electromagnetic irradiation is imposed to break up the metal precursor molecules and form metal radicals. The metal radicals react with the oxygen terminated surface to form an atomic layer of metal oxide on the surface of the substrate.

In the illustrative example where the substrate has an oxide deposited on the surface of the substrate, the following structure is present:



For pretreatment, the substrate having oxides deposited on the surface is dipped in a weak hydrogen fluoride (HF) solution to create a hydrogen-terminated surface as shown in the

following structure:



5

The substrate having the hydrogen-terminated surface is then placed in a reactor which is maintained at a low temperature and high vacuum. An oxygen containing gas is introduced into the reactor above the substrate. Examples of the oxygen containing gas include (but not limited to)  $\text{O}_2$ ,  $\text{NO}$ ,  $\text{N}_2\text{O}$ ,  $\text{H}_2\text{O}$ ,  $\text{H}_2\text{O}_2$ , and the like. The oxygen containing gas can be introduced into the reactor in various ways and is delivered about the substrate. For example, the oxygen containing gas can be introduced into the reactor from the top or the sidewall of the reactor. The hydrogen-terminated surface is exposed to the oxygen containing gas. However, the oxygen containing gas does not react with the hydrogen at the substrate surface due to the low temperature and pressure maintained in the reactor.

15 To activate the reaction, a first pulse of electromagnetic irradiation is initiated which activates the oxygen containing gas above the surface of the substrate to form oxygen radicals. Any form of electromagnetic irradiation can be used, and preferably the electromagnetic irradiation is pulsed. For example, electromagnetic irradiation can be photo UV, magnetic field, or microwave energy. The selection of electromagnetic irradiation depends on the application and the type of film to be deposited. While microwave energy may create an electrical field across the substrate, photo UV does not create an electrical field and thus is preferable for applications where electrical fields should be avoided. The electromagnetic irradiation can emanate from the top of the reactor, or may be focused to a particular localized region or area on the substrate. Alternatively, in a multiple wafer reactor, a side wall scanning laser can be used to sequentially expose multiple substrates to the electromagnetic radiation pulses. A side wall scanning laser is advantageous in a multiple wafer reactor. Alternately, a focused source of electromagnetic radiation can be used to activate the PALD process on selected areas of the substrate (i.e. direct write).

25

In the exemplary embodiment, the oxygen radicals formed react with hydrogen at the

irradiation is imposed as a pulse. For example, the electromagnetic irradiation can be photo UV, magnetic field, and microwave. The selection of electromagnetic irradiation depends on the application and the type of film to be removed. While microwave energy may create electrical field across the substrate, photo UV does not create electrical field and thus is good for applications where electrical field should be avoided. The electromagnetic irradiation can be imposed from the top of the reactor to a particular local area above the substrate. Alternatively, in a multiple wafer reactor, a side wall scanning laser can be used to impose electromagnetic irradiation to the multiple substrates sequentially. A side wall scanning laser is advantageous in a multiple wafer reactor. Alternately, a focused source of electromagnetic radiation can be used to activate the PALR process on selected areas of the substrate (i.e. "direct write" removal). The radical species react with the surface to form volatile compounds which are removed from the reactor. The process can be repeated to remove atomic layers of films at low temperatures.

Another exemplary embodiment of the present invention is illustrated in FIGs. 4A to 4J which show sequential steps in detail. In this example atomic layer exchange is carried out with photo-assist to form a gate dielectric having an equivalent oxide thickness (EOT) of 5. Atomic layer exchange is carried out to modify the chemistry of the film surface. As shown in FIG. 4A, a silicon wafer having a hydrogen passivated surface is provided. Next, an oxygen source is conveyed to the chamber about the wafer. The oxygen source is activated by electromagnetic radiation as shown in FIG. 5C. The activated oxygen source undergoes a surface reaction with the wafer and exchanges hydrogen atoms with oxygen atoms to form one, or one half, atomic layer of oxide on the wafer as shown in FIG. 5D. The reactor is then purged.

Next, a precursor which will produce the desired gate dielectric material is conveyed to the chamber. In this example, a Hf containing source is the precursor. The Hf precursor is activated by a pulse of electromagnetic radiation, such as a UV photo pulse, under low temperature as shown in FIGs. 4F and 4G. Atomic layer deposition occurs on the surface of the wafer as shown in FIG 4H, and then the reactor is purged, preferably with the assistance of argon gas.

To form the dielectric, in this example Hafnium oxide, an oxygen source is again conveyed to the reactor as shown in FIG. 4I. The oxygen source is activated by a photo pulse,



and atomic layer deposition occurs to form a  $\text{HfO}_2$  layer on the surface of the wafer. The oxygen source is purged (FIG. 4J) from the reactor and the process may be repeated to form additional atomic layers as desired.

As described above, atomic layer exchange takes place between free radicals or molecules in the gas phase and the wafer surface. Diffusion of these gaseous precursors through the wafer surface may be controlled by a number of parameters, including temperature, pulse time, chamber pressure, molecule size and reactivity - to avoid multilayer atomic exchange.

The photo-assisted atomic layer deposition and removal method of the present invention has broad applications. For example, the present invention can be used to etch metals and dielectrics, generate photolithographic masks, and improve resolution of liquid crystal displays, among other applications. Additionally, atomic layer removal of the present invention may be used for reducing final film thicknesses and/or removing undesired surface roughness prior to forming gate electrodes. High quality high- $\kappa$  dielectric films can be deposited with selected ALD precursors at low deposition temperature with photo activation. Examples of suitable liquid Hf and liquid Zr precursors are shown in FIGS. 5 and 6, respectively. The silicon - high  $\kappa$  dielectric interface may be controlled by atomic layer exchange of the present invention along with low temperature ALD high  $\kappa$  dielectric processes. Additional applications for high -  $\kappa$  gate dielectric applications are shown in FIG. 7.

While the present invention is disclosed by reference to the preferred embodiments and examples detailed above, it is to be understood that these examples are intended in an illustrative rather than limiting sense, as it is contemplated that modifications and combinations will readily occur to those skilled in the art, which modifications and combinations will be within the scope of the invention and the scope of the appended claims.

CLAIMS

What is claimed:

- 5 1. A method of depositing a film on a substrate, comprising:  
providing a substrate having an film deposited on the surface of the substrate;  
pre-treating the substrate to form a stable, activated surface on the substrate;  
introducing a first gas into the reactor at a low temperature and pressure;  
providing a first pulse of electromagnetic irradiation about the substrate to form radicals  
10 species from said first gas;  
reacting the radicals with the stable, activated surface to form an radical terminated  
surface on the substrate;  
introducing a second gas into the reactor at a low temperature and pressure; and  
providing a second pulse of electromagnetic irradiation about the substrate to form  
15 different radicals species from said second gas; and  
reacting the different radicals with the radical terminated surface to form a layer of film  
on the substrate.
- 20 2. A method of removing a film on a substrate, comprising:  
providing a substrate having an film deposited on the surface of the substrate;  
pretreating the substrate to form a stable, activated surface on the substrate;  
introducing a gas into the reactor at a low temperature and pressure;  
providing a first pulse of electromagnetic irradiation above said substrate to form radical  
species from said gas; and  
25 reacting the radicals with the stable, activated surface to form a volatile compound which  
is removed from the reactor.

ABSTRACT

A method and system for photo-assisted atomic layer deposition and removal of a dielectric film are provided. A substrate with an activated surface is placed into a reactor at low temperature and high vacuum. A gas is introduced into the reactor. An electromagnetic pulse is imposed into the reactor to form radical species of the gas. The radical species react with the activated surface. A second gas is introduced and a second electromagnetic pulse is imposed. The radicals of the second gas react with the surface to deposit a film. Alternately, the gaseous species can be chosen to produce radicals that result in the removal of material from the surface.

10




FIG - 1




FIG - 2




FIG - 3

# Atomic Layer Exchange For 5 EOT Gate Dielectric





FIG-4A

50 45 40 35 30 25 20 15 10 5 0

# Atomic Layer Exchange For 5 EOT Gate Dielectric




FIG - 4B

# Atomic Layer Exchange For 5 EOT Gate Dielectric




FIG - 4C



# Atomic Layer Exchange For 5 EOT Gate Dielectric




FIG-40

# Atomic Layer Exchange For 5 EOT Gate Dielectric




FIG-4E

# Atomic Layer Exchange For 5 EOT Gate Dielectric




FIG-4F

# Atomic Layer Exchange For 5 EOT Gate Dielectric





FIG - 4G

# Atomic Layer Exchange For 5 EOT Gate Dielectric

ALD Reaction  
and  
Ar Purge



H Passivated  
Si Wafer  
Surface




FIG - 44

# Atomic Layer Exchange For 5 EOT Gate Dielectric







FIG-4I

# Atomic Layer Exchange For 5 EOT Gate Dielectric



F/G-45

# New Liquid Hf Precursors for ALD Applications

	Formula	Appearance	b.p.(T <sub>sub</sub> )
TDMAH	$\text{Hf}[\text{N}(\text{CH}_3)_2]_4$	Light yellow crystal	85 /0.1mmHg
TEMAH	$\text{Hf}[\text{C}_2\text{H}_5\text{N}(\text{CH}_3)]_4$	Slightly yellow liquid	80 /0.1mmHg
TDEAH	$\text{Hf}[\text{N}(\text{C}_2\text{H}_5)_2]_4$	Light Yellow liquid	115 /0.1mmHg

FIG-5





- Nano-laminates with multiple films and surfaces create more interface traps therefore not recommended for advanced gate applications.
  - Bulk or Bi-Layer ALD Films are recommended.
  - At Least One Atomic layer of SiO<sub>2</sub> is needed at the interface to control mobility.
  - High-K Materials must be stable and do not react with H<sub>2</sub> treatment.
- High-K material oxides can react with H<sub>2</sub> and turn to metal films.
- Deposition process must take place at the lowest possible temperature in order to prevent diffusion of elements and minimize an interface depletion.
  - ALD Precursors must be in liquid or gas form. Solid precursors are not recommended for volume production due to change in their partial pressure while they being are consumed.
  - ALD Precursors should not decompose as in CVD reactions.
  - Atomic, Layer by Layer growth is essential. Island type growth is not desired.
  - Low temperature Deposition without any PLASMA assistance.

Fig - 7

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**